

SYMALIT ECTFE 1000 is a semi-crystalline unreinforced fluoropolymer combining good mechanical, thermal and electrical properties with excellent chemical resistance. It also shows good resistance to high-energy radiation.

SYMALIT ECTFE 1000 is a versatile engineering material especially suitable for the manufacture of components for the petro-chemical, chemical, metallurgical, paper, textile, semiconductor, pharmaceutical and nuclear industries.

Physical properties (indicative values [■])

PROPERTIES	Test methods	Units	VALUES
Colour	-	-	natural (white)
Density	ASTM D 792	g/cm ³	1.65 - 1.71
Water absorption:			
- after 24 h immersion in water of 23°C	ASTM D 570	%	< 0.01
Thermal Properties			
Melting temperature	ASTM D 3418	°C	220 - 230
Glass transition temperature	DMTA	°C	85
Thermal conductivity at 23°C	ASTM D 433	W/(K.m)	0.151 - 0.157
Coefficient of linear thermal expansion:			
- average value between 23 and 100°C	ASTM D 696	m/(m.K)	5 - 10 x 10 ⁻⁵
Specific Heat Capacity	DSC	kJ/(kg.K)	0.95 - 1.26
Vicat Point B	DIN 53460/B	°C	116
Temperature of deflection under load:			
- method A: 1.82 MPa	ISO 75	°C	65
Max. allowable service temperature in air:			
- continuously : for min. 20,000 h	-	°C	150
Min. service temperature	-	°C	-76
Flammability:			
- Oxygen Index	ASTM D 2863	%	52
- according to UL 94	-	-	V-0
Mechanical Properties at 23°C			
Tension test:			
- tensile stress at yield	ISO 527-1/-2	MPa	29 - 30
- tensile strength	ISO 527-1/-2	MPa	46 - 55
- tensile strain at break	ISO 527-1/-2	%	250 - 300
- tensile modulus of elasticity	ISO 527-1/-2	MPa	1600 - 1700
Flexural Modulus	ISO178	MPa	1600 - 1700
Compression test:			
- compressive stress	ASTM D 695	MPa	29 - 30
Izod impact strength - notched	ISO 180	J/m	no break
Hardness Shore D	ISO 868		75
Abrasion Resistance Taber	Taber CS 17/1 kg	mg/1000 rev.	5
Friction Coefficient:			
- static	ASTM D 1894		0.2
- dynamic	ASTM D 1894		0.2
Electrical Properties at 23 °C			
Dielectric strength	ASTM D 149	kV/mm	14
Volume resistivity	ASTM D 257	Ohm.cm	> 10 ¹⁶
Surface resistivity	ASTM D 257	Ohm	> 10 ¹⁵
Dielectric constant at 1 MHz	ASTM D 150	-	2.5
Dielectric dissipation factor tan δ at 1 MHz	ASTM D 150	-	0.013

Note: 1 g/cm³ = 1,000 kg/m³; 1 MPa = 1 N/mm²; 1 kV/mm = 1 MV/m.

AVAILABILITY

Round Rods: Ø on request - **Sheets and Plates:** Thicknesses 1.5 - 25.4 mm - **Lining Laminates:** Thickness 1.5 - 4 mm

Welding Rods: Thicknesses 3 - 4 mm

SYMALIT[®] is a registered trademark of the **Quadrant Group**.

All information supplied by or on behalf of Quadrant Engineering Plastic Products in relation to its products, in any form, is supported by research and believed to be reliable, but Quadrant Engineering Plastic Products assumes no liability whatsoever in respect of application, processing or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use of the aforementioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to Quadrant Engineering Plastic Products for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the aforementioned information or products by the buyer.

Quadrant Engineering Plastic Products

global leader in engineering plastics for machining

www.quadrantplastics.com

Legend:

All values are results of tests, made by raw material suppliers and Quadrant EPP AG and from literature. Most of the figures given in the table are results of tests made on extruded or injection molded sheets. Lining laminates can only be tested, if the fabric backing is removed carefully by machining. Otherwise the fabric backing influences the results. These values are average values and can vary depending on product, production method and specimen preparation.

All tests are done according to the standards mentioned in the table or equivalent standards of other organisations (ISO, ASTM, DIN).

- This table is a valuable help in the choice of a material. The data listed here fall within a normal range of product properties of dry material. **However they are not guaranteed and they should not be used to establish material specification limits nor used alone as the basis of design.**